

GRES PORCELLANATO . PORCELAIN STONEWARE

GRÈS CÉRAMÉ . FEINSTEINZEUG

UNI EN 14411 Bla Allegato G (ISO 13006)

www.cottopetrus.it

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft		Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	GRANITI
	Lunghezza e larghezza / Lenght and width Longuer et largeur / Länge und breite	UNI EN ISO 10545-2	N ≥ 15 cm	Conforme Corresponding Conforme Entsprechend
	Spessore / Thickness Epaisseur / Stärke		% ± 0,6 Non Rect. ± 0,3 Rect	
	Rettilineità spigoli / Straightness of sides Rectitude des arêtes / Kantengeradheit		(mm) ± 2,0 Non Rect. ± 1,0 Rect	
	Ortogonalità / Rectangularity Orthogonalité / Rechtwinkligkeit		± 5	
	Planarità / Surface flatness Planeité de surface / Ebenflächigkeit		± 0,5 Non Rect. ± 0,3 Rect	
	Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität	UNI EN ISO 10545-2	Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen	Conforme Corresponding Conforme Entsprechend
	Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	UNI EN ISO 10545-3	≤ 0,5% Individual max 0,6%	≤ 0,5%
	Sforzo di Rottura / Breaking strength Effort de rupture / Bruchkraft (≥ 7,5 mm thickness)	UNI EN ISO 10545-4	S ≥ 1300 N	S ≥ 1300 N
	Resistenza alla flessione / Modulus of Rupture Résistance à la flexion / Biegefestigkeit		R ≥ 35 N/mm ²	R ≥ 35 N/mm ²
	Resistenza all'abrasione (metodo PEI) Abrasion resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)	UNI EN ISO 10545-7	Segnala la classe di abrasione e i cicli superati Report abrasion class and cycles passed	NERO PEI II GRIGIO - BEIGE PEI IV CARRARA PEI IV
	Resistenza al gelo Resistance to frost Résistance aux gel Frostbeständigkeit	UNI EN ISO 10545-12	Richiesto Required	Non gelivo Frost-proof Non gélifs Frostsicher
	Resistenza ai prodotti chimici Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien	UNI EN ISO 10545-13	Resistenza a basse concentrazioni di acidi e alcali Resistance to low concentrations of acids and alkalis Secondo la classificazione indicata dal fabbricante Manufacturer is to state classification	LA
			Resistenza ad alte concentrazioni di acidi e alcali Resistance to high concentrations of acids and alkalis Metodo di prova disponibile Test method available	HA
			Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B	A
	Resistenza alle macchie Staining resistance Résistance aux taches Widerstand gegen Fleckenbildung	UNI EN ISO 10545-14	Min. 3	Conforme Corresponding Conforme Entsprechend
	Resistenza agli sbalzi termici Thermal shock resistance Résistance aux écarts de température Temperaturwechselbeständigkeit	UNI EN ISO 10545-9	Metodo di prova disponibile Test method available	Resiste Resistant Résiste Widerstandsfähig
Caratteristiche accessorie / Additional features				
	Stabilità dei colori Colours stability Stabilité des couleurs Farbbeständigkeit	DIN 51094	Colorazione Stabile Stable coloring	Conforme Corresponding Conforme Entsprechend
Caratteristiche di sicurezza / Safety characteristics				
	Resistenza allo scivolamento ** Slip resistance Résistance au glissement Rutschemmende Eigenschaft	METODO B.C.R.A.	μ > 0,40	-
		DIN EN 16165	ANNEX A Test della rampa a piedi nudi / Classe dichiarata Barefoot ramp test / Declared Class Méthode de la rampe pieds nus / Classe déclarée Methode der schiefen Ebene, barfuß / Angegebene Klasse	-
			ANNEX B Test della rampa a piedi calzati / Classe dichiarata Shod ramp test / Declared Class Rampe avec chaussures / Classe déclarée Methode der schiefen Ebene, mit Schuhwerk / Angegebene Klasse	R11
		DCOF (ANSI A 326.3)	> 0,42	-